

4.2	oxide induced crack closure	65
4.2.1	Wells CTOD relationship	65
4.2.2	Lankford CTOD relationship	70
4.2.3	Practical application	73
5	CREEP CRACKING	77
5.1	Creep cracking at high frequencies	77
5.1.1	Observations	77
5.1.2	Discussion	81
5.2	Creep crack initiation assessment	84
5.2.1	TDFAD Approach	84
5.2.2	Pineau approach	88
6	KITAGAWA-TAKAHASHI DIAGRAM	95
6.1	Comparison of K-T diagrams	95
6.1.1	Influence of stress ratio	95
6.1.2	Influence of temperature	98
6.1.3	Comparison of modified K-T diagrams for different materials	99
6.2	Discussion	100
6.2.1	Sensitivity of a_0 to R and temperature	100
6.2.2	Relationship between a_0 and forward plastic zone size	100
6.2.3	Influence of crack closure on physically short crack length	101
6.3	Practical implications	102
7	CONCLUSIONS AND OUTLOOK	117
7.1	Conclusions	117
7.2	Outlook	119
8	APPENDICES	121
8.1	Ansys APDL code for DCPD method	121
8.2	Summary of performed tests	124
8.2.1	FCG tests	124
8.2.2	Plain specimen fatigue limit tests	127
8.2.3	$da/dN(\Delta K)$ responses for FCG tests	132
	BIBLIOGRAPHY	141

LIST OF FIGURES

Figure 2.1	Three fracture modes of a structure	6
Figure 2.2	Two types of cracks, both subjected to a remote tension σ . The dimensionless shape function $Y = 1$ for the center crack, and $Y = 1.12$ for the edge crack.	6
Figure 2.3	The relationship between ΔK and da/dN in high cycle fatigue crack growth	7
Figure 2.4	The influence of the temperature and the frequency to the fatigue crack growth behaviour	8
Figure 2.5	The influence of the stress ratio to the fatigue crack growth behaviour	9
Figure 2.6	The influence of temperature, frequency, R and environment to ΔK_{th} for 1CrMoV steel at 550 °C [7, 8]	9
Figure 2.7	Opening and closing of the crack tip with or without crack closure at ① minimum load ② maximum load ③ closure load ④ minimum load ⑤ opening load	10
Figure 2.8	Plastic deformation in the vicinity of the crack tip under plane stress condition.	12
Figure 2.9	An explanation of plastic induced crack closure under plane strain conditions when surface roughness is involved.	12
Figure 2.10	The deformation of volume elements near the crack under plane strain condition and with or without constraint. When the deformation is constrained by the elastically deformed material outside the plastic zone, the volume elements shift towards the crack tip.	13
Figure 2.11	Deformation in the vicinity of the crack tip under (a) plane stress and (b) plane strain conditions. The figure is taken from [11]	14
Figure 2.12	Schematic illustration of roughness induced crack closure	15

Figure 2.13	Measurement of the oxide layer thickness for the 2.25Cr-1Mo steel at different conditions. The thickness of the oxide layer increases with decreasing crack growth rate at $R = 0.05$, while the stress ratio has no effect to the oxide layer thickness at $R = 0.75$. The figure is taken from [31]	17
Figure 2.14	The parabolic relationship between the oxide layer thickness and time in fatigue crack propagation. The figure is taken from [37].	17
Figure 2.15	Crack open and close in the case of (a) $K_{min} < K_{cl}$, (b) $K_{min} > K_{cl}$	19
Figure 2.16	The theoretical relationship between ΔK_{th} and R	21
Figure 2.17	The relationship between ΔK_{th} and R , where in low- R region the curve is constructed according to Equation (2.11), and in high- R region the curve is constructed according to Equation (2.12).	22
Figure 2.18	Some experimental results of ΔK_{th} values tested at $R = 0.1$ for different materials at temperatures between room temperature and 700°C.	23
Figure 2.19	SN curve of steels, with σ_e the fatigue endurance limit	25
Figure 2.20	Typical SN curve of steels, with σ_e the fatigue endurance limit	26
Figure 2.21	The Goodman curve and Gerber curve	26
Figure 2.22	The relationships between da/dN and ΔK for short cracks and long cracks, where short cracks propagate with a relatively high speed at ΔK below ΔK_{th} for long cracks. The crack propagation rate of short cracks decreases at firstly with increasing ΔK , after which the propagation rate increases again and finally merges into the $da/dN(\Delta K)$ relationship for long cracks.	27
Figure 2.23	The development of a crack from nucleation to becoming a long crack. The short crack regime is divided into three regimes, namely microstructurally, mechanically and physically short cracks. The figure is taken from [62].	28
Figure 2.24	The Kitagawa-Takahashi (black solid) and modified Kitagawa-Takahashi (red dashed) diagram.	30

Figure 2.25	The Kitagawa-Takahashi diagram showing the range of microstructurally and physically short crack.	31
Figure 2.26	Summary of k_p^{UB} values as a function of $1/T$ for oxide scale development in air [73]	33
Figure 2.27	The composition of oxide scales for the 1%Cr steel at elevated temperatures	34
Figure 2.28	The composition of oxide scales for the 9%Cr steel at elevated temperatures	34
Figure 2.29	The composition of oxide scales for the 18%Cr steel at elevated temperatures	35
Figure 2.30	Two criteria diagram for creep crack initiation assessment	36
Figure 2.31	An illustration of $R_{0.2}^c$, σ_{ref} and the corresponding ϵ_{ref} in an isochronous stress strain curve	38
Figure 2.32	A schematic TDFAD	39
Figure 2.33	Variation of creep toughness parameters K_{mat}^c and K_{Ii} with time, and influence of section size. The figure is taken from [48].	40
Figure 2.34	Experimental results of creep crack initiation time T_i and the corresponding C_0^* tested at various specimens at 575°C, 600°C and 650°C [81]	42
Figure 2.35	Schematic representation of Stage I and Stage II CCG behaviour. Figure is from [89]	44
Figure 3.1	Two control modes for ΔK_{th} determination tests, both with ΔK decreasing	49
Figure 3.2	Two examples of FCG tests with ΔK -decreasing procedures. The K_{max} control mode was adopted for the high- R test, while the R control mode was adopted for the low- R test. The K_{max} control mode is not applicable for the low- R test mainly because of the big variability of R during the ΔK -decreasing procedure.	50
Figure 3.3	The dimension of the adopted CT specimen and the arrangement of the current and potential leads	52
Figure 3.4	The FEM model for the derivation of the relationship between potential drop and crack extension.	53
Figure 3.5	The potential field calculated by the simulation with crack extension of 3mm.	53

Figure 3.6	The derived relationship between a/W and V/V_f by an electrical field simulation with a 2-D CT specimen geometry.	54
Figure 3.7	The arrangement for the FCG tests.	54
Figure 3.8	The dimensions of the adopted fatigue specimen with circular cross section and 5mm diameter.	55
Figure 3.9	The arrangement for the fatigue limit tests.	56
Figure 3.10	An example of staircase test data collection	57
Figure 3.11	Prediction of σ_e at different R using Gerber diagram. σ_e values at different R are represented by the intersection point between Gerber diagram and dashed equal- R lines.	57
Figure 3.12	A schematic illustration of the FIB drilling technique	59
Figure 3.13	Oxide layer observed in SEM with tilt angle 52° after polishing the vertical face of the FIB trench	59
Figure 3.14	An example of FIB measurement of oxide layer thickness. The oxide layer thickness was measured at 8 different spots that are equally distributed, and the oxide layer thickness is calculated as the average of the measured thickness.	60
Figure 3.15	The calculated k_p values of the three steels at different temperatures and their corresponding upper bound values.	60
Figure 4.1	The values of crack length calibrated by DCPD method and measured by optical microscope. The calibrated values are in good agreement with the actual crack length.	62
Figure 4.2	Relationship between ΔK_{Ih} and R of the three steels at 550°C . The loading frequencies are between 40Hz to 60Hz.	63
Figure 4.3	ΔK_{Ih} of 9%Cr and 18%Cr steels at different R at different elevated temperatures. The loading frequencies are between 40Hz to 60Hz.	64
Figure 4.4	The fracture surface of a 9%Cr steel specimen observed from the optical microscope and SEM	66
Figure 4.5	A schematic illustration of crack tip status at K_{min} and $K > K_{min}$ in high- R cyclic loading.	67
Figure 4.6	The relationship between $dCTOD_{min}$ and k_p/f at $R=0.9$	70

Figure 4.7	Comparison of predicted and observed [48, 53] values of ΔK_{th}^{ox}	71
Figure 4.8	A schematic illustration of forward and cyclic plastic zone in front of the crack tip in a 2-D plane. It should be noticed that the shape of plastic zones is simplified as a circle here, while an accurate shape of the plastic zone is more complicated.	72
Figure 4.9	Predicted and measured ΔK_{th}^{ox} values.	74
Figure 4.10	The model for the calculation of maximum allowable crack depth in the rotor made from 1%Cr or 9%Cr steel.	74
Figure 5.1	An example of a FCG test for 9%Cr steel at 550°C where creep cracking was involved.	78
Figure 5.2	SEM inspection of the specimen fracture surface	79
Figure 5.3	Three types of $da/dN(\Delta K)$ response and the corresponding fracture surfaces for FCG tests which involve crack tip creep cracking. (a) and (b) are the $da/dN(\Delta K)$ responses and the corresponding fracture surfaces for type 1 behaviour, (c) and (d) are the $da/dN(\Delta K)$ responses and the corresponding fracture surfaces for type 2 behaviour, and (e) and (f) are the $da/dN(\Delta K)$ responses and the corresponding fracture surfaces for type 3 behaviour.	80
Figure 5.4	Flow chart for the estimation of C^* values from a , W and P for a given specimen geometry and a given K	82
Figure 5.5	The relationship between a and C^* for $K = 30\text{MPa}\sqrt{m}$. C^* increases with crack length.	83
Figure 5.6	Type 1 and 2 $da/dN(\Delta K)$ responses with the corresponding creep crack growth rate during the ΔK decreasing FCG test.	85
Figure 5.7	TDFAD approach with three candidates, namely $K_{Ii}(12.5)$, $K_{Ii}(25)$ and $K_{mat}^c(CT25)$ as creep toughness. CCI is only conservatively predicted with $K_{Ii}(12.5)$	87

Figure 5.8	TDFAD of 1%Cr, 9%Cr and 18%Cr steels loaded in quasi-stationary state for 24 hours at temperatures between 550°C and 650°C. The filled data points indicate that creep cracking is observed from the fatigue crack tip on the fracture surface, while the unfilled data points indicate that no evidence of creep cracking is observed on the fracture surface.	91	Figure 6.8	Comparison between the a_0 values at different temperatures and different R for three steels.	113
Figure 5.9	The fracture surface of the CT specimen which corresponds to the abnormal assessment data point for the 9%Cr steel at 600 °C.	92	Figure 6.9	The values of a_0 and ρ for the the three steels at elevated temperatures independent of R	114
Figure 5.10	Assessment of creep crack initiation using $t_i(C_0^*)$ relationships of three steels. The black lines denote the original $t_i(C_0^*)$ relationships obtained in various sources [86, 88], while the dashed lines denote the approximate $t_i(C_0^*)$ relationships for the 12.5mm thickness CT specimen. The blue cross points denote the $t_i(C_0^*)$ relationships derived from $t(K_{II})$ values of 12.5mm thick CT specimens.	93	Figure 6.11	The relationship between a_0 and ρ' , where where $\rho' = \rho \cdot (R_{p,0.2}/R_m)^2$	115
Figure 6.1	The influence of stress ratio on the K-T diagrams (solid curves) and modified K-T diagrams for the three steels at different temperatures and different stress ratios	97	Figure 6.12	The relationship between a_p and R for the three steels at elevated temperatures. Low R corresponds to low values of a_p , while high R corresponds to relatively higher values of a_p	115
Figure 6.2	The relationship between a_0 and R for the three steels at elevated temperatures. Low R corresponds to low values of a_0 , while high R corresponds to relatively higher values of a_0	98	Figure 6.13	The assessment of non-propagating crack at high R and low R	116
Figure 6.3	The modified K-T diagrams for the 1%Cr steel at different temperatures and different stress ratios . . .	105	Figure 8.1	$da/dN(\Delta K)$ responses for 1%Cr steel at 550°C.	133
Figure 6.4	The modified K-T diagrams for the 9%Cr steel at different temperatures and different stress ratios . . .	107	Figure 8.2	$da/dN(\Delta K)$ responses for 9%Cr steel at 550°C.	134
Figure 6.5	The modified K-T diagrams for the 18%Cr steel at different temperatures and different stress ratios . . .	109	Figure 8.3	$da/dN(\Delta K)$ responses for 9%Cr steel at 600°C.	135
Figure 6.6	Comparison of the modified K-T diagrams (solid curves) for the three project steels for different R at 550°C.	111	Figure 8.4	$da/dN(\Delta K)$ responses for 9%Cr steel at room temperature.	136
Figure 6.7	The relationship between a_0 and R for three steels at room temperature. a_0 values are all below 1mm which are similar to the reported a_0 sizes in the literatures [63, 70, 109, 110].	112	Figure 8.5	$da/dN(\Delta K)$ responses for 18%Cr steel at 550°C.	137
			Figure 8.6	$da/dN(\Delta K)$ responses for 18%Cr steel at 650°C.	138
			Figure 8.7	$da/dN(\Delta K)$ responses for 18%Cr steel at room temperature.	139